



## **NAPSTAR GLOBAL FZC**

### **Rubber Processing Oil**

The primary characteristics of aromatic hydrocarbons is the presence of the double mix ring carbon structure. Aromatic extracts procured from selected refineries and suitably blended to meet stringent specifications, are used for compounding batches to manufacture Tyres, Tubes, Hoses, Calender sheets etc.

### **Specification:**

<b>PROPERTY</b>	<b>TEST METHOD</b>	<b>RANGE</b>
Kinematics Viscosity @100°C (cSt)	ASTM D-445	45Min
Density @ 15°C	ASTM D-1298	1015
Flash Point (°C)	ASTM D-92	225Min
Color	ASTM D-1500	8 Max
Pour Point (°C)	ASTM D-97	24 Max
Aniline Point (°C)	IP-2	30
Sulphur Content (%Wt)	ASTM D-2622	3.4
ASH Content (%Wt)	ASTM D-482	0.02